

## **AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

### **LISTING OF CLAIMS:**

1. (Original) A self-aligning roller bearing in which double row rollers as rolling elements are arranged rollably between an inner ring and an outer ring in a circumferential direction,

wherein a roughness of an outer ring raceway surface formed on an inner peripheral surface of the outer ring is made larger than a roughness of an inner ring raceway surface formed on an outer peripheral surface of the inner ring, and

an average roughness  $R_a$  of the outer ring raceway surface is set within  $0.1 \mu\text{m} \leq R_a \leq 0.5 \mu\text{m}$  in an axial direction and a circumferential direction, and a roughness parameter  $S$  that is defined by

$$S = \frac{1}{n} \sum_{i=1}^n S_i$$

where  $n$  is a number of peaks of the roughness of a roughness curve indicating the roughness of the outer ring raceway surface, and

$S_i$  is an interval between neighboring peaks of the roughness curve is set within  $0 < S_i \leq 20 \mu\text{m}$ .

2. (Original) A self-aligning roller bearing in which double row rollers as rolling elements are arranged rollably between an inner ring and an outer ring in a circumferential direction,

wherein a roughness of an outer ring raceway surface formed on an inner peripheral surface of the outer ring is made larger than a roughness of an inner ring raceway surface formed on an outer peripheral surface of the inner ring, and

an average roughness  $R_a$  of the outer ring raceway surface is set within  $0.1 \mu\text{m} \leq R_a \leq 0.5 \mu\text{m}$  in an axial direction and a circumferential direction, an average roughness of a rolling contact surface of the rolling element is set to  $R_a < 0.1 \mu\text{m}$ , and an average roughness of the inner ring raceway surface is set to  $R_a < 0.15 \mu\text{m}$ .

3. (Original) A self-aligning roller bearing in which double row rollers as rolling elements are arranged rollably between an inner ring and an outer ring in a circumferential direction,

wherein a roughness of an outer ring raceway surface formed on an inner peripheral surface of the outer ring is made larger than a roughness of an inner ring raceway surface formed on an outer peripheral surface of the inner ring, and

an inequality  $Rao/Rai \geq 1.5$  is satisfied where  $Rai$  is an upper limit value of a roughness range on the inner ring raceway surface on a center line and  $Rao$  is a lower limit value of a roughness range on the inner ring raceway surface on a center line, and a difference of a retained austenite content  $\gamma R$  between the rolling elements and at least any one of the inner ring and the outer ring is set to 3 % or more in volume ratio.

4. (Original) A self-aligning roller bearing according to claim 1, wherein an average roughness of a rolling contact surface of the rolling element is set to  $R_a < 0.1 \mu\text{m}$ , and an average roughness of the inner ring raceway surface is set to  $R_a < 0.15 \mu\text{m}$ .

5. (Original) A self-aligning roller bearing according to claim 1, wherein an inequality  $Rao/Rai \geq 1.5$  is satisfied where Rai is an upper limit value of a roughness range on the inner ring raceway surface on a center line and Rao is a lower limit value of a roughness range on the inner ring raceway surface on a center line, and a difference of a retained austenite content  $\gamma R$  between the rolling elements and at least any one of the inner ring and the outer ring is set to 3 % or more in volume ratio.

6. (Original) A self-aligning roller bearing according to claim 2, wherein an inequality  $Rao/Rai \geq 1.5$  is satisfied where Rai is an upper limit value of a roughness range on the inner ring raceway surface on a center line and Rao is a lower limit value of a roughness range on the inner ring raceway surface on a center line, and a difference of a retained austenite content  $\gamma R$  between the rolling elements and at least any one of the inner ring and the outer ring is set to 3 % or more in volume ratio.

7. (Original) A self-aligning roller bearing according to claim 4, wherein an inequality  $Rao/Rai \geq 1.5$  is satisfied where Rai is an upper limit value of a roughness range on the inner ring raceway surface on a center line and Rao is a lower limit value of a roughness range on the inner ring raceway surface on a center line, and a difference of a retained austenite content  $\gamma R$  between the rolling elements and at least any one of the inner ring and the outer ring is set to 3 % or more in volume ratio.

8. (Currently Amended) A self-aligning roller bearing according to claim 1, wherein the average roughness  $Ra$  of the outer ring raceway surface is set within  $0.1 \mu\text{m} \leq Ra \leq 0.5 \mu\text{m}$  in the axial direction and the circumferential direction in ranges of  $b_1/(B/2) \leq 0.9$ ,  $b_2/(B/2) \leq 0.9$  and in a measured length of 0.1 mm to 1.0 mm where  $B$  is a

width of the outer ring and  $b_1, b_2$  are a distance from both end surfaces of the outer ring respectively, and the roughness parameter  $S$  is set within  $0 < S \leq 20 \mu\text{m}$ .

9. (Original) A self-aligning roller bearing according to claim 1, wherein the outer ring raceway surface has machining traces that intersect with each other and the machining traces are formed by a super finishing.

10. (Original) A self-aligning roller bearing according to claim 2, wherein the outer ring raceway surface has machining traces that intersect with each other and the machining traces are formed by a super finishing.

11. (Original) A self-aligning roller bearing according to claim 3, wherein the outer ring raceway surface has machining traces that intersect with each other and the machining traces are formed by a super finishing.